



LUNDHS

Crafted by nature
Refined for living

Technical Data Sheet

Lundhs Antique

*Lundhs Antique has a unique compound of clear blue/purple crystals on brown background.
Previous trading name for this material was Labrador Antique.*

Technical Properties	Standard	Mean Values
stone name:	ns-en 12407	monzonite (larvikite)
structure:		coarse grained
texture:		oriented feldspar crystals with lustre
compressive strength:	ns-en 1926	195 mpa
flexural strength:	ns-en 12372	13 mpa
flexural strength: (after 48 frost cycles)	ns-en 12371	13.1 mpa
abrasion resistance, böhme:	din 52 1081	6.4 cm ³ / 50 cm ²
abrasion resistance, böhme:	ns-en 14157 (b) ²	7102 mm ³
abrasion resistance, wide wheel:	ns-en 14157 (a) ³	17.0 mm
water absorption:	ns-en 13755	0.07% weight
apparent density:	ns-en 1936	2700 kg/m ³
open porosity:	ns-en 1936	0.2%
breaking load at dowel holes:	ns-en 13364	2930 n
slip resistance: (honed surface)	ns-en 14231	63 srv (dry) 3 srv (wet)
rupture energy, thickness 30 mm:	ns-en 14158	3.8 j
resistance to ageing by thermal shock:	ns-en 14066	no visual changes. no weight loss
petrographic composition:	ns-en 12407	feldspar 85% pyroxene 9% chlorite 3% opaques 3%

the tests have been performed according to technical requirements given in e.g. ns-en 1467 (rough blocks), ns-en 1469 (slabs for cladding), ns-en 12057 (modular tiles) and ns-en 12058 (slabs for floors and stairs). test results from sintef building and infrastructure (2006), (www.sintef.no)

¹ Based on thickness measurements.
² Based on weight measurements.
³ Reference method for natural stone.

Box 2051, Stubberud
N-3255 Larvik, Norway

t: +47 33 12 11 64
f: +47 33 18 23 34
m: info@lundhs.no
www.lundhs.no